一、喷砂、吸砂胶管 Blast and blast suction hose

1、帘线喷砂胶管 Cord sandblast rubber hose

用途：供装置在风压喷砂机上对金属表面喷砂除锈及打磨用。

特点：内胶层具有良好的耐磨性，外胶层具有良好的耐老化性和耐磨性能。胶管爆破压力不低于工作压力的四倍。

USE：Used in wind–pressured sand–spraying machine to get rid of the rust by spraying sand.

CHARACTERISTICS：The inner layer is wear–resistance and the outer layer is good at anti–aging and wear–resistance. The burst pressure of the hose is four times or higher than the working pressure.

内径英制尺寸 inside diameter	内径公制尺寸 inside diameter	帘线层数 layer	工作压力 Working pressure	最大长度 Max length
Inch	mm	/	bar	m
3/4	19±0.4	2/4	12	61±1%
7/8	22±0.4	2/4	12	61±1%
1	25±0.8	2/4	12	61±1%
1–1/4	32±1.0	2/4	12	61±1%
1–1/2	38±1.0	2/4	12	61±1%
2	51±1.2	2/4	12	61±1%
2–1/2	64±1.2	4	12	61±1%
3	76±1.4	4	12	61±1%
4	102±1.6	4	12	61±1%



内径、外径、长度、压力、外胶颜色，可根据客户要求生产（3/4＂–14＂）。

耐磨性能：50mm³/65mm³/110mm³，符合ISO4649：2002

The inner diameter、outer diameter, length、pressure and cover colour can be produced according to the customer's demand（3/4＂–14＂）.

Abrasion resistance：50mm³/65mm³/110mm³ ,according to ISO 4649:2002

2、钢编喷砂胶管 Wire braid sandblast rubber hose

用途：供装置在风压喷砂机上喷砂（或铁丸）除锈及清扫金属铸件、土建工程、输送水泥砂浆用。

特点：内胶层具有良好的耐磨性，外胶层具有良好的耐老化性和耐磨性能。胶管承压性能高，管体不变形，胶管爆破压力不低于工作压力的四倍。

USE：Used in wind–pressured sand–spraying machine to get rid of the rust and clean metal by spraying sand (or with iron ball),–civil engineering and convey cement motar and so on.

CHARACTERISTICS：The inner layer is wear–resistance and the outer layer is good at anti–aging and wear–resistance. The hose can assure high pressure and it will be not deformation,The burst pressure of the hose is four times or higher than the working pressure.

内径英制尺寸 inside diameter	内径公制尺寸 inside diameter	工作压力 Working pressure	最大长度 Max length
Inch	mm	bar	m
1	25±0.8	69	40±1%
1–1/4	32±1.0	43	40±1%
1–1/2	38±1.0	35	40±1%
2	51±1.2	26	40±1%
2–1/2	64±1.2	25	40±1%
3	76±1.4	25	40±1%
4	102±1.6	18	40±1%



内径、外径、长度、压力、外胶颜色，可根据客户要求生产（1/2＂–4＂）。

耐磨性能：50mm³/65mm³/110mm³，符合ISO4649：2002

The inner diameter、outer diameter, length、pressure and cover colour can be produced according to the customer's demand.（1/2＂–4＂）

Abrasion resistance：50mm³/65mm³/110mm³ ,according to ISO 4649:2002

3、帘线吸砂胶管 Cord sandblast suction rubber hose

用途：适用于抽吸矿砂、河沙、煤屑以及谷类（稻、麦、玉米）等固体物质或颗物料。

特点：内胶层具有良好的弹性及耐磨性，外胶层具有良好的耐老化性和耐磨性能，管体有优良的曲挠性。管体具有承受正压和负压的双重性能，在承受真空度为–80kpa（600mm汞柱）的条件下能正常使用，胶管爆破压力不低于工作压力的四倍。

USE：Used to suction solid materials or grain materials such as mineral sand,river sand,coal dust and bits of coal and cereal (rice,wheat,corn)etc.

CHARACTERISTICS：The inner layer of the hose has good flexibility and wear–resistance, while the outer layer is excellently anti–aging and wear–resistance. The hose has good bending performance,The hose has the double properties of bearing both the positive and negative pressure can be used normally under the pressure of –80kpa (600mm mercury) at the vacuum. The burst pressure of the hose is four times or higher than the working pressure.

内径英制尺寸 inside diameter	内径公制尺寸 inside diameter	帘线层数 layer	工作压力 Working pressure	最大长度 Max length
Inch	mm	/	bar	m
1	25±0.8	4	10	61±1%
1–1/4	32±1.0	4	10	61±1%
1–1/2	38±1.0	4	10	61±1%
2	51±1.2	4	10	61±1%
2–1/2	64±1.2	4	10	61±1%
3	76±1.4	4	10	61±1%
4	102±1.6	4	10	61±1%
4–1/2	115±1.6	4	10	20±1%
5	127±1.6	4	10	20±1%
6	152±2.0	4	10	20±1%
8	203±2.5	4	10	20±1%
10	254±3.0	4	10	10±1%
12	305±3.0	6	10	10±1%



内径、外径、长度、压力、外胶颜色，可根据客户要求生产（3/4＂–14＂）。

耐磨性能：50mm³/65mm³/110mm³，符合ISO4649：2002

The inner diameter、outer diameter, length、pressure and cover colour can be produced according to the customer's demand（3/4＂–14＂）.

Abrasion resistance：50mm³/65mm³/110mm³ ,according to ISO 4649:2002

4、编织喷砂胶管（布纹面/光面） Braid sandblast rubber hose(Wrapped/smooth)

用途：供装置在风压喷砂机上对金属表面喷砂除锈及打磨用。

特点：内胶层具有良好的耐磨性，外胶层具有良好的耐老化性和耐磨性能。胶管爆破压力不低于工作压力的四倍。

USE：Used in wind–pressured sand–spraying machine to get rid of the rust by spraying sand.

CHARACTERISTICS：The inner layer is wear–resistance and the outer layer is good at anti–aging and wear–resistance. The burst pressure of the hose is four times or higher than the working pressure.

内径英制尺寸 inside diameter	内径公制尺寸 inside diameter	工作压力 Working pressure	最大长度 Max length
Inch	mm	bar	m
1/2	12.7±0.6	12	100±1%
5/8	16±0.6	12	100±1%
3/4	19±0.6	12	100±1%
1	25±0.6	12	100±1%



内径、外径、长度、压力、外胶颜色，可根据客户要求生产（1/2＂–1＂）。

耐磨性能：50mm³/65mm³/110mm³，符合ISO4649：2002

The inner diameter、outer diameter, length、pressure and cover colour can be produced according to the customer's demand（1/2＂–1＂）.

Abrasion resistance：50mm³/65mm³/110mm³, according to ISO 4649:2002